

Instrumental Issues concerning Surface Diffraction that exploits Coherence

Ian Robinson

Garth Williams

Mark Pfeifer

Ivan Vartanians

Franz Pfeiffer

Ross Harder

Meng Liang

University of Illinois


Sector 34-ID-C

Workshop on Surface and
Interface Science at the
ESRF


Outline

- Coherence in Diffraction
- How to Solve the **Phase** Problem
- Nanocrystal Shapes
- Real space **Phase** objects
- Instrumental issues at Sector 34
- Use of Optics in CXD

Longitudinal Coherence



Lateral (Transverse) Coherence





Als-Nielsen and McMorrow (2001)

Coherence at the APS or ESRF

Typical of 3rd Generation (undulator) Synchrotron Source


Coherence of	ξ_{VER}	ξ_{HORIZ}	ξ_{LONG}	Flux
Raw Undulator	35 μm	9 μm	0.004 μm	2×10^{12}
Si(111) Monochromator	35 μm	9 μm	1 μm	1×10^{10}
C(111) Monochromator	35 μm	9 μm	3 μm	3×10^9

Coherent region defined by slits




Diffuse Scattering acquires Structure using CXD

Real Space




Reciprocal Space




Size-dependent Melting of Au Particles

P. Buffat and J-P. Borel, Phys. Rev. A 2287-97 (1975)




Chemical Synthesis of Nanocrystals




- Reactants introduced rapidly
- High temperature solvent
- Surfactant/organic capping agent
- Square superlattice (200nm scale)

C. B. Murray, IBM J. Res. & Dev. **45**
47 (2001)




SEMS


- Au blanket film
- Quartz substrate
- Annealed at 950°C for 70 hrs.



Lensless X-ray Microscope



Generic “Error Reduction” method




J. R. Fienup *Appl. Opt.* 21 2758 (1982)

R. W. Gerchberg and W. O. Saxton *Optik* 35 237 (1972)

Real-space Constraints in Crystallography




R. P. Millane, J. Opt. Soc Am. A **13** 725 (1996)

- ‘Positivity’ and ‘Atomicity’ constraints (Sayre)
- Finite **support**, molecular envelope
- Solvent flattening/Molecular replacement
- Non-crystallographic symmetry
- Non-uniqueness is ‘pathologically rare’ ($d > 1$)
- Uses memory to avoid stagnation (Fienup HIO)





Symmetrized Data and two best fits

Chisq=0.0005




2D Reconstructions


chisquare = 0.0005






3D Diffraction Method












3D Diffraction Data 1 micron Au crystal






Slices through
plan view SEM:






Twinning in deformed FCC metals

J. Wulff, "Structure and Property of Materials III" (1965)




■ $\sim 10\mu\text{m}$
Cu


Reconstruction of Pb Nanocrystal



3D reconstruction of Pb nanocrystals



3D Phase Images of Lead Nanocrystals




- 500nm Pb crystals grown **in-situ** in UHV system at APS (Argonne) on a SiO₂ support (vertical).


- 3D coherent X-ray diffraction data is inverted into hemi-spherical cross-sectional slices.

- These images are colored according to the **phase** of the density, which changes abruptly at an internal boundary.
- This plane is identified as a single **deformation fault** in the crystal.


Lensless X-ray Microscope




Chemically Synthesized Silver Nanocubes





Yugang Sun and Younan Xia,
Science 298 2177 (2003)



Reconstruction of 2-fold View




←→
200nm



Miscentered Non-Centrosymmetric Reciprocal Space Slice




$$A_q \neq A_{\bar{q}}^*$$





Real-space phase.

What can we expect to see?





$$A(\bar{q}_o + \bar{q}_z) = \sum_i \underbrace{\sum_z \rho(x, y, z)}_{u_i(x, y)} e^{2\pi i \bar{q}_z \cdot \bar{z}_i} e^{2\pi i (\bar{q}_o) \cdot \bar{r}_i}$$







Data and Data Mask ($>7\%$ Max)

Experiment






Direct Space Result (1000 Iterations)




Reciprocal Space Result (1000 iterations)

Experiment






1D and 2D Quantum Dot Arrays

Zhenyang Zhong, G. Bauer, Johannes Kepler Universität Linz




Vary Coherence (model)

I. A. Vartanyants and I. K. Robinson,
J. Sync. Rad. **10** 409 (2003)




202 Diffraction from Ge QD array

with G. Bauer, Z. Zhong and T. H. Metzger






Result of fitting GISAXS data



I. K. Robinson, ESRF Workshop, Oct 2004

Images from Fitting GISAXS


with Jeff Onken



AFM


Mask used
as support

Diffraction pattern under constraint





34-ID-C Capabilities

- Beam-splitting mirror
 - cuts out half of central cone
- Double Crystal Monochromator
 - Diamond, Si(111) and Si(220)
- Coarse and Fine coherence slits
 - UHV Roller-blade design
- Long-arm Microcontrole Diffractometer




I. K. Robinson, ESRF Workshop, Oct 2004







I. K. Robinson, ESRF Workshop, Oct 2004

Smallest Beam using Slits (9keV)




$$y(x) = x + \frac{\lambda d}{x}$$





Window as a Secondary Source




$$L_T = \frac{\lambda D}{2\sigma}$$

$$L_{T2} = \frac{\lambda D}{2\sigma} \frac{\left(1 - \frac{d_1}{D}\right)}{\left(1 + \frac{\sigma' D}{\sigma} \frac{d_1}{D}\right)}$$

Vert ~50
Horiz ~3

Two Components to MCF

Coherence




- Width of narrow component is very sensitive to location of window
- Amplitude of narrow component depends on level of diffuse scattering from window
- Amplitude increases with distance (for phase object)



BN Coating on Sector 34 Window


protects against corrosion of Window by pink beam




BN spray coating

Coating removed

Au Nanocrystal CXD at Sector 34



BN-coated window



BN removed Sept 2002

Topography of Diamonds

Measured at 33-BM on Kodak dental film



Second crystal, as mounted




After loosening clamping screws

Switch to Si(111) monochromator

Scan table to watch topography



Diamond



Silicon

Conclusions and Outlook

- Inversion of CXD to spatial images
- Internal structure of Au Nanocrystals in 3D
- Phasing by computation instead of lens
- Possible to obtain **complex** images
- Images of Quantum Dots in an array
- Intimate relationship of samples and beamline