

# Surface Structure determination by Synchrotron X-ray Diffraction

I. K. Robinson

University College, London  
and Diamond Light Source

ICTP School on Synchrotron Radiation

May 25th, 2006


# Important Contributions from

Sanjit Ghose	Urbana
Peter Bennett	Arizona
Franz Himpsel	Wisconsin
Jia Wang	Brookhaven
Ratko Adzic	Brookhaven
Ben Ocko	Brookhaven
Sebastien Boutet	Urbana
Marie-Claire St Lager	CNRS
Pierre Dolle	CNRS
Maurizio deSantis	CNRS
Robert Baudouing-Savois	CNRS
X16A, X22A	NSLS
BM32	ESRF


# Menu of Topics

- Crystal Truncation Rods
- Au quantum nanowires on Stepped Si
- Reconstruction of Pt(110)1x5
- Facetting of Cu(115) to Cu(104)
- Au ‘physisorption’ on Si(111)7x7
- Deep subsurface strain in Pt(111)/CO
- GSAXS and C-GSAXS new methods


# Origin of Truncation Rods




$$\begin{aligned} F_{CTR} &= \sum_{n=0}^{\infty} A_n \\ &= \sum_{n=0}^{\infty} f_L e^{inqa} \\ &= \frac{f_L}{1 - e^{iqa}} \end{aligned}$$




# CTR as Convolution




# Surfaces and Interfaces



Isolated monolayer




Surface of Crystal



Crystal-Crystal Interface

# Diffuse Scattering from Si Wafer



Unpolished wafer

40 microns removed

N. Kashiwagara, J. Harada and M. Ogino, J. Appl. Phys 54 2706 (1983)

# Diffraction as a Surface Integral

**Die äußere Form der Kristalle  
in ihrem Einfluß auf die Interferenzerscheinungen  
an Raumgittern**

**Von M. v. Laue**

Annalen der Physik [5] 26 55 (1936)







FIG. 200




“Stacheln”

# CTR is Sensitive to Surface Structure





# X16A Surface X-ray Diffraction operating since 1987 ...



I. K. Robinson ICTP school on SR

# Menu of Topics



- Crystal Truncation Rods
- Au quantum nanowires on Stepped Si
- Reconstruction of Pt(110) $1 \times 5$
- Facetting of Cu(115) to Cu(104)
- Au ‘physisorption’ on Si(111) $7 \times 7$
- Deep subsurface strain in Pt(111)/CO
- GSAXS and C-GSAXS new methods



I. K. Robinson ICTP school on SR


# Crystallography of Stepped Surfaces

Silicon (111)



Si(557) surface

100l on SR




# Alignment is Straightforward

CALCULATED PARAMETERS:

	A	B	C	ALFA	BETA	GAMMA				
REC:	0.164431	1.63392	0.116412	90.06	90.03	89.93				
DIR:	38.2118	3.84548	53.9736	89.94	89.97	90.07				
	H	K	L	TTH	TH	PHI	CHI	ALP	CTS	ERROR
OR 1 =	12.0	0.0	3.0	21.938	112.920	50.308	-1.137	3.841	22456	0.0027
OR 2 =	-5.0	1.0	7.0	20.284	97.018	307.482	-2.259	9.179	20719	0.0018
OR 3 =	14.0	0.0	20.0	26.411	113.142	40.844	-1.290	26.483	13639	0.0009
OR 4 =	12.0	2.0	3.0	43.135	110.470	4.520	-2.092	4.313	12772	0.0009

Lambda = 1.20913 Å,  $wv = 5.19647$ , Energy = 10.2542 keV (FIXED)  
Five-Circle Mode using alm = 2 and bem = 2:

Centered Orthorhombic unit cell contains two steps.




$3 \times 1$  clean  
surface


$1 \times 1$  surface  
with 0.2ML Au  
at 600C

# STM of Si(557)/Au

R. Losio, et. al., Phys. Rev. Lett. 86 4632 (2001)


1.9 nm






# Phasing by a Single Heavy Atom


H. B. Dyer, Acta Cryst. 4 42 (1951)



Cysteinylglycine  
sodium iodide





Patterson




Electron density

# X-Z Patterson of Au/Si(557)






(a) A coordinate system with a vertical y-axis and a horizontal x-axis.




(b) A coordinate system with a vertical z-axis and a horizontal x-axis.



(c)

# Comparison with STM





# Menu of Topics


- Crystal Truncation Rods
- Au quantum nanowires on Stepped Si
- **Reconstruction of Pt(110)1x5**
- Facetting of Cu(115) to Cu(104)
- Au ‘physisorption’ on Si(111)7x7
- Deep subsurface strain in Pt(111)/CO
- GSAXS and C-GSAXS new methods

# Surface “Reconstruction”

RECONSTRUCTION




# Missing Row structure of FCC(110)



Pt(110) 1×3 Missing Row Structure





# Variations of Missing Row structure




# Pt(110) during heating at 600C

## Accompanied by segregation of Carbon



I. K. Robinson, P. J. Eng, C. Romainczyk  
and K. Kern, Surf. Sci. **367**  
105-112 (1996)

# BM32 measurements of Pt(110)1x5



# Homometric structures

$$F(Q) = F_1(Q)F_2(Q)$$

$$I(Q) = |F_1(Q)|^2|F_2(Q)|^2$$

$$F_j(Q) = \int \rho_j(x)e^{iqx} dx$$

$$F_j^*(Q) = \int \rho_j(-x)e^{iqx} dx$$


$$I(Q) = \left| \int \underline{\rho_1(x) \circ \rho_2(x)} e^{iqx} dx \right|^2$$

$$I(Q) = \left| \int \underline{\rho_1(-x) \circ \rho_2(x)} e^{iqx} dx \right|^2$$

Identical diffraction  
from two structures  
whenever the structure  
factor is factorizable


# Homometric structures II

Convolution of two structures without mirror symmetry



# Displacements in final model

## Pt(110)1x5 “hill” model




Chisq=2.7


90% hill, 10% valley

7% “1x1”


(a)



(b)



(c)





## Pt(110)1x3

# Menu of Topics

- Crystal Truncation Rods
- Au quantum nanowires on Stepped Si
- Reconstruction of Pt(110)1x5
- Facetting of Cu(115) to Cu(104)
- Au ‘physisorption’ on Si(111)7x7
- Deep subsurface strain in Pt(111)/CO
- GSAXS and C-GSAXS new methods



# Cu(115) after Oxidation: STM

S. Reiter and E. Taglauer, Surf. Sci. 367 33 (1996)




# Cu(115) after Oxidation: X16A

Don Walko, UIUC PhD  
Dissertation (2000)



son ICTP school on SR


# Re-index CTRs for Cu(104) facets




# Surface Structures of Cu(104)-O

E. Vlieg, S. M. Driver, P. Goettkindt, P. J. Knight, W. Liu, J. Luedecke, K. A. Mitchell, V. Murashov, I. K. Robinson, S. A. de Vries and D. P. Woodruff, *Surface Science* **516** 16-32 (2002)



Overlayer




Missing Row 4




Missing Row 2



Perderau and Rhead






Robinson et al



Woodruff et al

# In-plane and CTR data at Daresbury







# Problems with refinement of structure

O row number	Cu row number	Unconstrained fit	Constrained fit LJ1	Constrained fit LJ2	Walko & Robinson	DFT calculation
1	1	1.86	1.86	1.82	1.86	1.85
1	2	2.55	2.49	1.88	2.41	1.90
1	5	2.08	1.94	1.99	2.55	2.21
3	2	1.53	1.71	1.79	1.85	1.90
3	3	1.96	1.93	1.88	1.84	1.98
3	4	2.25	2.11	1.93	1.85	2.03
3	7	2.69	2.61	2.52	2.43	2.72

$$\chi^2=2.66$$

$$\chi^2=2.83$$




# Two Structures that fit the Data



LJ1

LJ2


# If we had measured ...




# Menu of Topics

- Crystal Truncation Rods
- Au quantum nanowires on Stepped Si
- Reconstruction of Pt(110)1x5
- Facetting of Cu(115) to Cu(104)
- Au ‘physisorption’ on Si(111)7x7
- Deep subsurface strain in Pt(111)/CO
- GSAXS and C-GSAXS new methods


# Si(111) 7x7 Reconstruction






# Dimer-Adatom-Stacking Fault model

K. Takayanagi by Transmission Electron Diffraction (1987)





# MEM inversion of X-ray data



L.D. Marks, Northwestern University




# Importance of Symmetry in Si(111)7x7



**p3m1 → Bulk Symmetry**



**p6mm → Surface Symmetry**




# Au physisorption on Si(111)7x7?

## Motivation

*To study the structure of self assembled metal nanostructures on Si(111)7x7 surface*

## Adsorption processes of Au on Si(111)7x7 surface




### Physisorption ( Physical absorption)

Adsorption in which the forces involved are inter-molecular (van der Waals forces), which do not involve a significant change in electronic orbital patterns of the species involved

### Chemisorption ( Chemical absorption)

Adsorption in which the forces involved are electronic valence forces of the same kind as those operating in the formation of chemical compounds, i.e., ionic and covalent bonds



# Au on Si(111) Phase Diagram




*D. Grozea, E. Bengu and L. D. Marks,  
Surf.Sci. 461, 23(2000)*

# Surface Symmetry

Real Space




Reciprocal Space



# L=1.5 symmetry breaking


Clean | 0.06ML Au




I. K. Robinson ICTP school on SR

# Structure factor data shows $p6mm$ symmetry breaking

Clean Si(111)7x7



0.06 ML Au on -Si(111)7x7



Agreement factor (☐) between equivalent reflections ( $L = 1.5$ ) averaged assuming  $P3m1$  and  $P6mm$  symmetry

## Agreement factor (☐)

### Sample Type

### P3m1


### P6mm

clean  
Au-0.06 ML  
Au-0.12 ML  
Au-0.18 ML

0.061  
0.079  
0.059  
0.056

0.076  
0.156  
0.110  
0.079

# Real Space 3D-Density Difference Map



$$\rho_{xyz}^{\text{obs}} = \sum_{hkl} (|F_{hkl}^{\text{obs}}| - |F_{hkl}^c|) e^{i\alpha_{hkl}^c} \exp(-2\pi(hx + ky + lz))$$

$z \sim$  adatom height

Cho & Kaxiras Surf. Sci.  
 396 L261 (1988)




Fig. 1. Schematic top-view representation of a portion of the Si(111) reconstruction containing three Si adatoms (large black circles) and one rest-atom (grey circle) as well as the substrate atoms directly bonded to those (smaller open circles). The sites where the adsorbate atoms are placed are indicated by the numbers 1–6. These sites are used for the energy plots in Fig. 2.





Fig. 2. Plots of the adsorbate atom energies along the six sites defined in Fig. 1 (from left to right the six sites are  $T_1$ ,  $H_3$ -type,  $B_2$ -type,  $T_4$ -type,  $B'_2$ -type and  $H'_3$ -type). The energies are relative to the lowest energy sites for each adsorbate atom (see Table 1).

# Potential from Anisotropic DWF

$$\begin{aligned} \text{One Particle Potential } V(x,y) &= -k_B T [\text{Log} \{ \text{FT (DWF)} \}] \\ &= -25.84 [\text{Log} \{ \text{FT (DWF)} \}] \text{ meV} \quad \text{at 300 K} \end{aligned}$$

## Potential Energy within Basin of Attraction




*H. L. Meyerheim, I. K. Robinson and R. Schuster, Surf. Sci., 370,268(1997)*


I. K. Robinson ICTP school on SR

# Comparison with Theory

## Basin of Attraction



## Potential Energy within Basin of Attraction




*Kyeongjae Cho and Efthimios Kaxiras, Surf. Sci, 396, L261(1998)*

ICTP school on SR



# Menu of Topics

- Crystal Truncation Rods
- Au quantum nanowires on Stepped Si
- Reconstruction of Pt(110)1x5
- Facetting of Cu(115) to Cu(104)
- Au ‘physisorption’ on Si(111)7x7
- **Deep subsurface strain in Pt(111)/CO**
- GSAXS and C-GSAXS new methods


# CO dissolved in $\text{HClO}_4$ on Pt(111)




# CO reciprocal lattice, rt19



# Two inequivalent packings of 13 CO's into $rt(19)$ Pt(111) cell






This 'patch' model is the only one observed, by the CO peak positions




This 'ring' model is **not seen**.

# rt19×rt19 CO/Pt(111)



I. K. Robinson

# Top and Side Views of Model




Depth=1.8 layers

$D_7=0.28 \text{ \AA}$


$D_{6+6}=0.04 \text{ \AA}$

$\sigma_{\text{CO}}=0.3 \text{ \AA}$




# Fit of Model to CTR Data

Dashed curve is clean Pt(111)



# Fit of Model to Rt19 Data


Blue line has vertical relaxations turned off




# Menu of Topics

- Crystal Truncation Rods
- Au quantum nanowires on Stepped Si
- Reconstruction of Pt(110)1x5
- Facetting of Cu(115) to Cu(104)
- Au ‘physisorption’ on Si(111)7x7
- Deep subsurface strain in Pt(111)/CO
- **GSAXS and C-GSAXS new methods**

# Use of Grazing Incidence




# Longitudinal Coherence



$$L_L = \frac{1}{2} \frac{\lambda^2}{\Delta\lambda}$$

Als-Nielsen and McMorro (2001)

# Lateral (Transverse) Coherence



$$L_T = \frac{\lambda}{2} \frac{R}{D}$$



Als-Nielsen and McMorrow (2001)

# Coherence at the APS or ESRF

Typical of 3rd Generation (undulator) Synchrotron Source



Coherence of	$\xi_{\text{VER}}$	$\xi_{\text{HORIZ}}$	$\xi_{\text{LONG}}$	Flux
Raw Undulator	35 $\mu\text{m}$	9 $\mu\text{m}$	0.004 $\mu\text{m}$	$2 \times 10^{12}$
Si(111) Monochromator	35 $\mu\text{m}$	9 $\mu\text{m}$	1 $\mu\text{m}$	$1 \times 10^{10}$
C(111) Monochromator	35 $\mu\text{m}$	9 $\mu\text{m}$	3 $\mu\text{m}$	$3 \times 10^9$

Coherent region defined by slits





# Diffuse Scattering acquires Structure using CXD

Real Space




Reciprocal Space





# 34-ID-C Capabilities

- Beam-splitting mirror
  - cuts out half of central cone
- Double Crystal Monochromator
  - Diamond, Si(111) and Si(220)
- Coarse and Fine coherence slits
  - UHV Roller-blade design
- Long-arm Microcontrole Diffractometer



I. K. Robinson ICTP school on SR







I. K. Robinson ICTP school on SR

# Structure in “Yoneda” Peak

Grazing-exit diffraction from a 1000Å Au polycrystalline film




# Coherent “Yoneda” sample geometry




F. Pfeiffer, W. Zhang and I. K. Robinson,  
Applied Physics Letters 84 1847 (2004)


# Anisotropy of speckles



# Variation with entrance slit (microns)




# Angle series, $0.01^\circ$ steps




# Structure in “Yoneda” Peak

Grazing-exit diffraction from a 1000Å Au polycrystalline film



# Refraction by Gold Interface


$$\alpha_i' = \sqrt{\alpha_i^2 - 2\delta + 2i\beta}$$



$E=8.92\text{keV}$   
 $\delta=3.76\times 10^{-5}$   
 $\beta=2.9\times 10^{-6}$



# Competitive Grain Growth

C. V. Thompson, *Ann. Rev. Mat. Sci.* **30** 159 (2000)




# Model of grain correlations



- Density of film assumed uniform, except at location of grain boundaries
- Assume exponential size distribution in 3D
- Expect (Lorentzian)<sup>2</sup> lineshape



# Effect of refraction on lineshape




# Fits to (Lorentzian)<sup>2</sup> Profiles



Fit params: center (x,y), amplitude, width=0.0084,  $\alpha_i=0.011$

# Transmission Function



I. K. Robinson  $\alpha$  ICTP school on SR

# Transmission Function

- Refractive index

$$n = 1 - \delta + i\beta$$

- Snell's law

$$\cos \alpha = n \cos \alpha'$$

$$\alpha' = \text{Re}(\alpha') + i \text{Im}(\alpha')$$

$$\text{Re}(\alpha') = \sqrt{\frac{1}{2} \sqrt{(\alpha^2 - 2\delta)^2 + 4\beta^2} + \frac{1}{2}(\alpha^2 - 2\delta)}$$

$$\text{Im}(\alpha') = \sqrt{\frac{1}{2} \sqrt{(\alpha^2 - 2\delta)^2 + 4\beta^2} - \frac{1}{2}(\alpha^2 - 2\delta)}$$

- Amplitude Transmittivity


$$T = \frac{\alpha_T}{\alpha_I} = \frac{2\alpha}{\alpha + \alpha'}$$

Incidence



$$T(\vec{k}_1) = \frac{2\alpha_i}{\alpha_i + \alpha_i} = \text{const}$$

Exit

$$T(\vec{k}_2) = \frac{2\alpha_f}{\alpha_f + \alpha_f'}$$



# Simulations of CCD data



- Distorted-wave Born approximation

$$I \sim \left[ \frac{d\sigma}{d\Omega} \right]_{diff} \sim |T(\vec{k}_1)|^2 |T(\vec{k}_2)|^2 S(\vec{q})$$


- Assume

$$S(\vec{q}) = \frac{C}{(Q_{2D}^2 + W^2)^P}$$

$$= \frac{C}{((\eta Q_y)^2 + Q_z^2 + W^2)^P}$$


$$\text{or } \frac{C}{((\eta\Phi)^2 + (\alpha_i' + \alpha_f')^2 + W^2)^P} \quad \text{with } P=2$$

T=60<sup>0</sup>C




I. K. Robinson [CTP school on SR]

T=200<sup>0</sup>C



I. K. Robinson <sup>y</sup> ICTP school on SR

T=500<sup>0</sup>C



I. K. Robinson ICTP school on SR

# Future Outlook for GISAXS

- GISAXS explained by refraction +  $|T(\alpha)|$
- CGISAXS sees individual grain distribution
- Surface effects are relatively unimportant
- Invert diffraction pattern to an image
- Study evolution grain by grain
- Other metals, kinds of film
- Island to film transition

# Conclusions

- Crystal Truncation Rods
- Au quantum nanowires on Stepped Si
- Reconstruction of Pt(110)1x5
- Facetting of Cu(115) to Cu(104)
- Au 'physisorption' on Si(111)7x7
- Deep subsurface strain in Pt(111)/CO
- GSAXS and C-GSAXS new methods