

Inversion of Coherent Diffraction Images of Nanocrystals

- Ian Robinson
- Ivan Vartanyants Department of Physics
University of Illinois
- Franz Pfeiffer
- Mark Pfeifer
- Garth Williams SRI Coherence Workshop,
Berkeley, August 2003
- Curtis Benson


Outline

- Coherence in Diffraction
- Oversampling and the **Phase** Problem
- Nanocrystal Shapes
- How small can we go?
- Future Applications of CXD


Uses of Coherence in Diffraction

- Thermodynamic fluctuations
 - No ensemble average in CXD
- Probe of structure on **nm** scale
 - 1D, 2D and 3D
 - non-periodic object gives **continuous** $F(\mathbf{q})$
- **Oversampling** (in reciprocal space) permits solution of the **phase** problem

Lensless X-ray Microscope




Longitudinal Coherence



$$L_L = \frac{1}{2} \frac{\lambda^2}{\Delta\lambda}$$

Als-Nielsen and McMorro (2001)

Lateral (Transverse) Coherence



$$L_T = \frac{\lambda R}{2 D}$$



Als-Nielsen and McMorrow (2001)

Coherence at the APS

Typical of Undulator-based Synchrotron Source


Coherence of	ξ_{VER}	ξ_{HORIZ}	ξ_{LONG}	Flux
Raw Undulator	35 μm	9 μm	0.004 μm	2×10^{12}
Si(111) Monochromator	35 μm	9 μm	1 μm	1×10^{10}
C(111) Monochromator	35 μm	9 μm	3 μm	3×10^9

Coherent region defined by slits




Diffuse Scattering acquires Structure using CXD


Real Space



Reciprocal Space



Generic “Error Reduction” method



J. R. Fienup *Appl. Opt.* 21 2758 (1982)


R. W. Gerchberg and W. O. Saxton *Optik* 35 237 (1972)

Real-space Constraints in Crystallography


R. P. Millane, J. Opt. Soc Am. A 13 725 (1996)


- ‘Positivity’, ‘Atomicity’ constraints (Sayre)
- Solvent flattening
- Non-crystallographic symmetry
- Molecular replacement
- Finite **support** = molecular envelope
- Non-uniqueness is ‘pathologically rare’ ($d > 1$)



Convergence Trajectory



Phase Problem: Finite-size Effect









SEMS



- Au blanket film
- Quartz substrate
- Annealed at 950°C for 70 hrs.



Micron-sized gold crystal: (111) Bragg reflection






Imaging of Lattice Strains





Symmetrized Data and two best fits

Chisq=0.0005




2D Reconstructions

chisquare = 0.0005



Window as a Secondary Source




$$L_T = \frac{\lambda D}{2\sigma}$$

$$L_{T2} = \frac{\lambda D}{2\sigma} \frac{\left(1 - \frac{d_1}{D}\right)}{\left(1 + \frac{\sigma' D}{\sigma} \frac{d_1}{D}\right)}$$

Vert ~50
Horiz ~3


Two Components to MCF

Coherence




- Width of narrow component is very sensitive to location of window
- Amplitude of narrow component depends on level of diffuse scattering from window
- Amplitude increases with distance (for phase object)




3D Diffraction Method










3D Diffraction Data 1 micron Au crystal




* Center is Symmetric *



Slices through
plan view SEM:




CXD Beamline at APS Sector 34







Lensless X-ray Microscope





CXD from Silver Nanocubes





Yugang Sun and Younan Xia,
Science 298 2177 (2003)

Spherical and cylindrical waves




$\pi/4$

$\pi/2$





$\pi/4$ (x)

Reconstruction of Ag Nanocrystal





←→
200nm




0.7 μm Pb Nanocrystal

In-situ growth at APS sector 34




Incomplete Reconstruction can be Striped


0.5 micron Pb crystal on SiO₂ substrate



Result of “Patching” in 2D



Tomato Bushy Stunt Virus 1980



Conclusions and Outlook


- Diffuse scattering acquires fine structure
- Inversion of CXD demonstrated
- Internal structure in Au (not Pb, Ag) nanocrystals
- Preservation of coherence upon focussing
- Small crystals possible now;
- Single molecules one day with XFELs

Oversampling for Small Crystals

DFT connects N points with N reciprocal points

N points in $2a$:
 $N/2$ unknowns

N points in $3a$:
 $N/3$ unknowns



Always $N/2$ measurements

Reconstruction of Pb Nanocrystal

